



Product Description

High Barrier, Water Based, Environmentally Friendly, Nanocomposite Barrier Coating for Transparent Sustainable Packaging

Coating Formulation Properties

Property	Typical Value	Units
Oxygen Permeability	0.4 – 0.8 0.001 - 0.002	cc- μ /m ² -day-atm cc-mil/100 in ² -day-atm
Solid Content	13.0 – 15.0	%
pH	6 - 8	
Viscosity	30 - 50	cP (60 rpm, 79.2 sec ⁻¹)

- Provides source reduction and/or improved sustainability relative to EVOH & PVDC
- More cost effective than EVOH
- Excellent barrier up to 80% RH
- 2x the solid content of InMat's other products reducing the required drying time resulting in a higher speed coating process
- Excellent adhesion on all substrates eliminating the need for a primer
- Large enhancements of moisture barrier when coated on flexible packaging films
- Meets compostibility standards on bio-derived films
- Compliant with US and European food contact standards
- Targets dry food applications such as salty snacks, nuts, coffee
- Can be applied at high speeds using standard gravure coating methods
- No halogen, VOC's, or hazardous materials

InMat Inc.

216 Route 206 Suite 7, Hillsborough, NJ 08844 USA

(908) 874-7788 phone (908) 874-7672 fax

www.inmat.com



Nanolok™ WR 301409

Product Data Sheet

Product Description

High Barrier, Water Based, Environmentally Friendly, Nanocomposite Barrier Coating for Transparent Sustainable Packaging

Coated Film Properties

Base Film			PET 48 gauge	
Property	Units	RH		
Coating Thickness	micron		1.0 ± 0.1	
OTR 23C	cc/m ² -day-atm (cc/100 in ² -day-atm)	0%	0.4	(0.03)
		50%	0.6	(0.04)
		65%	0.6	(0.04)
		80%	14	(0.9)
MVTR 38C	0.8 um coating gm/m ² -day (gm/100 in ² -day)	85%	15	(0.9)
Adhesion	gm/inch	23C	>300	

Comparison of Coated and Uncoated Film

Film	Nanolok WR 301409 coating thickness (microns)	MVTR 38C, 85% RH (gm/m ² -day-atm)
PET 48 gauge	None	45
	0.8	15
BOPP 80 gauge	None	8
	1.1	3.5
PLA 80 gauge	None	275
	1.1	60